



Technical Data Sheet

DUCTSTRAP

CONSTRUCTION:

Tri layer laminate with 20grams per square metre of LDPE on each side of a 80 grams per square metre HDPE woven fabric.

TYPICAL PHYSICAL PROPERTIES:

Elongation at break: 16-18%

Tensile Strength: 270-300N/25mm

PACKING:

25mm x 50m on 76mm ID core, 48 rolls per carton, 80 cartons per pallet.

REMARKS:

1. The products should be stored at room temperature and be kept away wet and/or heat source.

PRECISION PAPER COATINGS PTY LTD PH: +61 (02) 9780 9000 FAX +61 (02) 9728 9966

The detail in this leaflet refers to average test results obtained in our laboratory out of samples chosen from average production. The results are purely indicative and it is recommended that the user independently ascertain suitability for the application.